



Vetonit Masonry Mortar

Premixed cementitious masonry mortar

Uses

- Masonry Mortar can be used internally or externally in wet & dry conditions onto block walls & rough surfaces.
- Masonry Mortar can be used for cement & concrete blocks and panels.
- Masonry Mortar can be used for filling walls and joints

Product Description

Masonry Mortar is a cement based coat composed of hydraulic binders, selected aggregates and high performance additives. It is supplied as a dry powder in pre-weighed bags ready to use on site, which requires only addition of clean water to produce cohesive mortar. Masonry Mortar is a premium quality product contains special adhesion additive. Masonry Mortar can be applied in thickness from 5 mm to 50 mm.

Advantages

- Factory controlled pre-blend ensures consistent high quality.
- Requires only addition of water on-site at the time of usage.
- Suitable for ME harsh weather conditions.
- When using the Silo system Easy application with uniform work flow enables high productivity & superior finishing.
- Strong adhesion on variety of concrete blocks.
- Strong bond in blocks & wall joints.
- Internal & external applications.
- Suitable for wet to dry conditions.

Standards Compliance

- ASTM C348 & C109
- ASTM C270 & C780
- BSEN 998-2, Type G
- ASTM C1072

Technical Data

Vetonit Masonry Mortar	Typical Values @ 25°C
Appearance	Grey colour Powder
Aggregate size	2.4 mm max
Wet density (Kg/Liter)	1.90 approx.
Pot time @ 25°C	1.5 hrs approx.
Setting Time @ 25°C	3 - 4 hrs
Compressive Strength @ 28 day (ASTM C109)	12.4 N/mm ²
Flexural Strength @ 28 day (ASTM C348)	3.0 N/mm ²
Flexural Bond Strength @ 28 day (ASTM C1072)	0.15 N/mm ²
Air Content	≤ 14%

Usage Instructions

Block Surface Preparation

The block surface should be sound, clean, free from loose material, grease, laitance, dirt, curing compound, etc.

Prior to Masonry Mortar application, wet the entire surfaces with clean potable water and surface should look damp at the time of Masonry Mortar application.

Mixing

Add to the mixing container 8 - 10 litres of water for each 50 Kg bag of Masonry Mortar. Add the powder to the water and mix with a mechanical plaster mixer or low speed electric drill fitted with a suitable paddle for 3-4 minutes, until a uniform, lump-free consistency is achieved.

Leave the mixed material to stand for 10 min and briefly remix without addition of water.

Manual mixing is allowed for small batch quantities by mixing for approx. 1-2 min, or when homogenous mix is achieved.

Application

Neutralize the suction of the block surface with water before applying mortar. Any excess water should be removed.

The masonry mortar is spread with trowel on the surface and joints where the blocks are to be mounted.

Fill joint in similar way as conventional sand/cement mortar.

After stiffening, the masonry mortar should be given a final smoothing to remove protrusions and eliminates undulations.

Cleaning

All tools should be cleaned immediately after finishing by water. Hardened materials can be cleaned mechanically.

Packaging & Coverage

Product	Pack Size
Masonry Mortar	50 Kg Bag

Product	Coverage
Masonry Mortar	15 L.M/ 10mm (Solid block 400x200x200 mm)
	22 L.M/ 10mm (Solid block 400x200x150 mm)
	31 L.M/ 10mm (Solid block 400x200x100 mm)

Stated consumptions data are for general guidance. Actual consumption depends on the nature of substrate, method of application and wastage.

LEGAL DISCLAIMER

Saveto endeavors to ensure that any advice, recommendations, information it may give, is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products, because it has no direct or continuous control over where or how its products are applied, whether or not in accordance with any advice, specification, recommendation or information given by us. Saveto has the right to change any of the specifications mentioned in the Technical data sheets upon its discretion without prior notification. Hard copies of TDSs are printed once or twice a year, while our technical data sheets are continuously being updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

Shelf Life & Storage

Original sealed bags of Masonry Mortar has a shelf life of 12 months provided it is stored clear of ground in a dry shaded place below 25°C.

Health & Safety

Masonry Mortar is highly alkaline therefore avoid direct contact with eyes or skin. It is recommended to use protective gloves and goggles during application. Any skin contact should be wash with soap & water. In case of eyes irritation, immediately wash with copious amount of clean cold water. Seek medical advice.

Masonry Mortar is non-flammable.

For further information, please refer to material safety data sheet.

Additional Information

Saveto manufactures a wide range of construction chemicals and specialty products for various applications divided into the following product groups:

- Concrete Repair, Grouts and Enhancement.
- Wall & Facade Systems.
- Flooring and Coating Systems.
- Sealants and Joints.
- Plasters & Renders.
- Putties & Finishes
- Tiling Systems
- Waterproofing.
- Primers & Ancillary Products.
- Specialty Products.

Saveto also provides various technical information such as CAD details, detailed method statements, specification clauses, application manuals, product selectors and technical support both in contractors and consultants offices as well as construction sites.

For further information on these products and systems kindly check our website or contact your local Saveto representative.